

# デルタ-AZ

株式会社 アサダ


<http://www.asada-metal.co.jp/>

株式会社アサダは、スチール、ワイヤー、ピアノ線、硬鋼線、ステンレス線などのばね材を主に取り扱っている線材・帯材の専門商社です。

進化したニューアロイコーティング

# デルタ-AZ


高耐食ばね用Zn-Al合金めっき鋼線



デルタ-AZは、亜鉛の犠牲防食作用とアルミニウムの高耐食性を兼ね備え、普通亜鉛めっきの2倍以上の高耐食性被膜を有します。又、テンパー処理等の高温下でも、FeZn合金層の異常発達や、めっき層の脆化がなく、抜群の耐熱性を発揮します。

時代のニーズに応える進化した素材。デルタ-AZは、ニューアロイコーティングとして可能性を大きく広げます。

## ■高耐食性を生むめっき層



デルタ-AZは、Zn-Al合金によるめっき層を持ち、腐食の初期段階に生成した腐食被膜がAlの役割により緻密な安定被膜を形成して下地を保護すること及び、素地の鋼を陰極的に保護することにより高耐食性を生み出す高度なめっき技術と高品質な伸線技術によって誕生した最先端技術製品です。

## ■デルタ-AZの標準線径と仕様

線径 mm	硬鋼線			ピアノ線		標準の荷姿	
	公差 (mm)	引張強さ (N/mm <sup>2</sup> )		公差 (mm)	引張強さ (N/mm <sup>2</sup> ) SWP-A	釜径 (mm)	質量 (kg)
		SW-B	SW-C				
1.00	±0.020	1720~1960	1960~2210	±0.010	2060~2260	400	50
1.20	±0.030	1670~1910	1910~2160	±0.015	2010~2210		
1.40		1620~1860	1860~2110		1960~2160		
1.60		1570~1810	1810~2060		1910~2110		
1.80		1520~1770	1770~2010		1860~2060		
2.00	±0.040	1470~1720	1720~1960	±0.020	1810~2010	550	100
2.30		1420~1670	1670~1910		1770~1960		
2.60		1370~1620	1620~1860		1720~1910		
2.90						600	125

※引張強さ:垂鉛めっき鋼線(JIS G 3548)のSWGD-2はSW-Bに相当し、SWGS-3はSW-Cに相当する。

※中間にある線径については、それより大きい線径の値を用いる。

## ■デルタ-AZの種類

記号	線径 mm	めっき付着量 g/m <sup>2</sup>	主な用途
AZ-α	1.00~2.90	40~120	耐疲労性を重視する精密ばね用
AZ-β		80~160	高耐食性を要求されるばね、フォーミング用

デルタ-AZは、広範囲な用途に応じられるよう、いろいろな品種を用意しておりますのでご相談ください。

特殊サイズや荷姿、また、ピアノ線B種相当品についても、ご相談に応じさせていただきます。

# W ジェイワイテックス株式会社

### ■本店・第一事業所

〒597-0054 大阪府貝塚市堤300番地  
TEL (072) 436-6802 FAX (072) 436-6812

### ■第二事業所

〒597-0015 大阪府貝塚市堀1丁目12番2号  
TEL (072) 431-1309 FAX (072) 430-2961

### ■関東事業所

〒321-0155 栃木県宇都宮市西川田南2丁目5番12号  
TEL (028) 658-0511 FAX (028) 658-0561

### ■営業本部・大阪支店

〒541-0053 大阪府大阪市中央区本町3丁目4番10号 野村ビル8階  
TEL (06) 6125-1861 FAX (06) 6125-1869

### ■東京支店

〒100-0005 東京都千代田区丸の内1丁目8番1号 丸の内トラストタワーN館17階  
TEL (03) 5288-8461 FAX (03) 5288-8505

### ■名古屋支店

〒450-0002 愛知県名古屋市中村区名駅4丁目2番25号 名古屋ビル東館9F  
TEL (052) 569-2685 FAX (052) 569-2686

### ■広島営業所

〒730-0013 広島県広島市中区八丁堀15番10号 セントラルビル8階  
TEL (082) 224-2766 FAX (082) 224-2788

### ■HEAD OFFICE :

300 TUTUMI, KAIZUKA, OSAKA 597-0054, JAPAN  
TEL:072-436-6802 FAX:072-436-6812

### ■SALES DEPT. OSAKA BRANCH :

NOMURA BUILDING 8FL  
4-10 HONMACHI 3-CHOME, CHUO-KU, OSAKA 541-0053, JAPAN  
TEL:06-6125-1861 FAX:06-6125-1869

### ■SALES DEPT. TOKYO BRANCH :

MARUNOUCHI TRUST TOWER NORTH 17FL  
8-1 MARUNOUCHI 1-CHOME, CHIYODA-KU, TOKYO 100-0005, JAPAN  
TEL:03-5288-8461 FAX:03-5288-8505

### ■SALES DEPT. NAGOYA BRANCH :

NAGOYA BUILDING EAST 9FL  
2-25 MEIEKI 4-CHOME, NAKAMURA-KU, NAGOYA 450-0002, JAPAN  
TEL:052-569-2685 FAX:052-569-2686

### ■HIROSHIMA SALES OFFICE:

CENTRAL BUILDING 8FL  
15-10 HATCHOBORI, NAKA-KU, HIROSHIMA 730-0013, JAPAN  
TEL:082-224-2766 FAX:082-224-2788